SPECIFICATION DATABASE



Norms: EN41 0 (2011-04)

CIE (15-2004)

Centre Pane 'u' Value - Double 6mm Annealed (1 x T+)





6 (16 Argon 90) 6

Coating: PLANITHERM TOTAL+ FG #3


Computed by: Oli Pringle

Computed on: 08/08/2024

Product catalog: United Kingdom

Luminous Factors

Glazing type



Simulated performance datas

Light Transmittance (TL)	78%
Outdoor Reflectance (RLe)	13%
Indoor Reflectance (RLi)	1 3 %
1	51144 0 (2014 04)
7 Energy Factors	EN41 0 (2011-04)
Transmittance (TE)	59%
Outdoor Reflectance (Ree)	21 %
Indoor Reflectance (Rei)	20%
Absorptance A1 (AE1)	9%
Absorptance A2 (AE2)	11%
Solar Factors	EN41 O (2011-04)
Solar Factor (g)	0.69
Shading Coefficient (SC)	0.79
☼ Thermal Transmission	EN 673-2011
Ug	1.2 W/(m2.K)
Angle relative to the vertical	O°
♦ Acoustics	EN 12758
Acoustic measurement values accord notified body	ling to EN 12758 and from
Rw (C;Ctr)	33 (-1; -5) dB
Ra	32 dB
Ra,tr	28 dB
STC (ASTM E413)	N/A
OITC (ASTM E1332)	N/A
Color Rendering	CIE (15-2004)
Transmission (Ra)	98.4
Reflection (Ra)	91 .7
Safety Class	EN 12600
Pendulum Body Resistance	NPD
Anti-Burglary	EN 356
Burglar Resistance	NPD
	INI D
Manufacturing Sizes	
Nominal Thickness	28.0 mm
Weight	30 kg/m²
Sustainability	
Carbon footprint	

The value is calculated regarding the composition computed based

EN 15804+ A2 (2019)

on the standard EN 15804+ A2 (2019) Global Warming Potential (GWP) - A1 -

(kg, CO₂ eq./m²) European average



Calumen® calculates the photometric characteristics and thermal transmission of glass using calculation algorithms which comply with the following standards: the European standards EN 410 and EN 673, the international standard ISO9050, the Japanese standard JIS R 31 06/3107 and the Korean standard KS L 251 4/2525. The functional output and calculation rules of Calumen® for standards EN 410 and EN 673 have been validated by TÜV Rheinland (report 89212153-01). The technical performances obtained according to these standards are provided for information only and are subject to amendment.

Only the values entered in the performance declaration available on the CE marking site of Saint-Gobain Glass are official.

The sound attenuation indices are measured under laboratory conditions according to the standards EN ISO 101 40 and EN 12758. The calculated indices are provided for information only. The accuracy for Rw index lies within a range of +1-248. The glass thickness calculations comply with the 2012 version of the DTU39-P4 description. The USER is responsible for