SPECIFICATION DATABASE



CIE (15-2004)

Centre Pane 'u' Value - 4/4/4 Toughened (2 x P1)





4 FT (14 Argon 90) 4 FT (14 Argon 90) 4 FT

Coating: PLANITHERM ONE II #3 / PLANITHERM ONE II #5

Computed by: Oli Pringle Computed on: 13/08/2024 Product catalog: United Kingdom Norms: FN41 0 (2011-04)

Glazing type



Simulated performance datas

Luminous Factors

Light Transmittance (TL)	57%
Outdoor Reflectance (RLe)	31 %
Indoor Reflectance (RLi)	32%
4 Energy Factors	EN41 O (2011-04)
Transmittance (TE)	33%
Outdoor Reflectance (Ree)	46%
Indoor Reflectance (Rei)	45%
Absorptance A1 (AE1)	8%
Absorptance A2 (AE2)	9%
Absorptance A3 (AE3)	4%
Solar Factors	EN41 O (2011-04)
Solar Factor (g)	0.41
Shading Coefficient (SC)	0.47
★ Thermal Transmission	EN 673-2011
Ug	0.6 W/(m2.K)
Angle relative to the vertical	O°
♠ Acoustics	EN 12758
Acoustic measurement values accord notified body	ing to EN 12758 and from
Rw (C;Ctr)	32 (-1; -4) dB
Ra	31 dB
Ra,tr	28 dB
STC (ASTM E413)	N/A
OITC (ASTM E1 332)	N/A
Color Rendering	CIE (15-2004)
Transmission (Ra)	96
Reflection (Ra)	94.6
Safety Class	EN 12600
Pendulum Body Resistance	1 C3/1 C3/1 C3
Anti-Burglary	EN 356
Burglar Resistance	NPD
Manufacturing Sizes	
Nominal Thickness	40.0 mm
Weight	30 kg/m²
Sustainability ■	
Carbon footprint	
The value is calculated regarding the on the standard EN 15804+ A2 (2019)	
Global Warming Potential (GWP) - A1	EN 15804+ A2 (2019)
A3	1



Calumen® calculates the photometric characteristics and thermal transmission of glass using calculation algorithms which comply with the following standards: the European standards EN 410 and EN 673, the international standard ISO9050, the Japanese standard JIS R 31 06/3107 and the Korean standard KS L 2514/2525. The functional output and calculation rules of Calumen® for standards EN 410 and EN 673 have been validated by TÜV Rheinland (report 89212153-01). The technical performances obtained according to these standards are provided for information only and are subject to amendment.

Only the values entered in the performance declaration available on the CE marking site of Saint-Gobain Glass are official.

The sound attenuation indices are measured under laboratory conditions according to the standards EN ISO 101 40 and EN 12758. The calculated indices are provided for information only. The accuracy for Rw index lies within a range of +1-248. The glass thickness calculations comply with the 2012 version of the DTU39-94 description. The USER is responsible for

(kg, CO₂ eq./m²) European average