

SPECIFICATION DATABASE

Centre Pane 'u' Value - 6.8mm/6mm Toughened (1 x T+)



33.2 (16 Argon 90) 6 FT

Coating: PLANITHERM TOTAL+ FG #5


Computed by: Oli Pringle




Computed on: 08/08/2024

Product catalog: United Kingdom











Norms: EN410 (2011-04)

Glazing type



	Glazing 1 PLANICLEAR (3mm) - Annealed PVB STANDARD (0.76mm) PLANICLEAR (3mm) - Annealed
	Cavity 1 Argon 90% 16 mm
	Glazing 2 PLANITHERM TOTAL+ FG PLANICLEAR (6mm) - Tempered

Simulated performance datas

	Luminous Factors	CIE (15-2004)
	Light Transmittance (TL)	78%
	Outdoor Reflectance (RLe)	13%
	Indoor Reflectance (RLi)	13%
	Energy Factors	EN410 (2011-04)
	Transmittance (TE)	57%
	Outdoor Reflectance (Ree)	17%
	Indoor Reflectance (Rei)	20%
	Absorptance A1 (AE1)	16%
	Absorptance A2 (AE2)	10%
	Solar Factors	EN410 (2011-04)
	Solar Factor (g)	0.66
	Shading Coefficient (SC)	0.75
	Thermal Transmission	EN673-2011
	Ug	1.2 W/(m2.K)
	Angle relative to the vertical	0°
	Acoustics	EN 12758
	<i>Acoustic simulated values</i>	
	Rw (C;Ctr)	37 (-2; -6) dB
	Ra	35 dB
	Ra,tr	31 dB
	STC (ASTM E413)	37
	OITC (ASTM E1332)	29
	Color Rendering	CIE (15-2004)
	Transmission (Ra)	98.4
	Reflection (Ra)	91.8
	Safety Class	EN 12600
	Pendulum Body Resistance	1B1/C2
	Anti-Burglary	EN 356
	Burglar Resistance	P1A/NPD
	Manufacturing Sizes	
	Nominal Thickness	28.8 mm
	Weight	31 kg/m ²
	Sustainability	
	Carbon footprint	
	<i>The value is calculated regarding the composition computed based on the standard EN 15804+ A2 (2019)</i>	
	Global Warming Potential (GWP) – A1-A3	EN 15804+ A2 (2019)
	(kg. CO ₂ eq./m ²) European average	56



Calumen® calculates the photometric characteristics and thermal transmission of glass using calculation algorithms which comply with the following standards: the European standards EN 410 and EN 673, the international standard ISO9050, the Japanese standard JIS R 3106/3107 and the Korean standard KS L 2514/2525. The functional output and calculation rules of Calumen® for standards EN 410 and EN 673 have been validated by TUV Rheinland (report 89212153-01). The technical performances obtained according to these standards are provided for information only and are subject to amendment.

Only the values entered in the performance declaration available on the CE marking site of Saint-Gobain Glass are official.

The sound attenuation indices are measured under laboratory conditions according to the standards EN ISO 10140 and EN 12758. The calculated indices are provided for information only. The accuracy for Rw index lies within a range of +/-2dB. The glass thickness calculations comply with the 2012 version of the DTU39-P4 description. The USER is responsible for ensuring that the correct calculation hypotheses are entered and the DTU39 is applied appropriately for the project concerned.